



CORONADO
P A I N T

SECTION NO. 7
ADS – 802
10 Line

Premium Gold Collection
100% Acrylic One Coat Flat House Paint
10 Line

| Type | Sheen | Theoretical Spread Rate | Recommended Application | Thinner | Clean Up |
|------------------|-------|-------------------------------|-----------------------------|-------------------------------|------------------|
| Acrylic | Flat | 300 - 400 Sq. Ft. Per Gallon* | Brush, Spray, Pad or Roller | Clean Water | Warm Soapy Water |
| Dry Time: | | Tack Free: 30 Minutes | Recoat: 4 Hours | Full Cure: 7 – 10 Days | |

| | | |
|--|--|---|
| PRODUCT NAME: 10 Line Premium Gold Collection 100% Acrylic One Coat Flat House Paint | An Acrylic Latex Flat House Paint which provides lasting service over new or previously painted surfaces in good condition. Acrylic Latex House Paint will provide a durable and protective finish on any properly prepared and primed exterior surface. | |
| WHERE TO USE: | Wood Hardboard Masonry Metal Galvanized | On exterior siding, foundations, fascia, shutters or retaining walls. |
| SURFACE PREPARATION: | <p>Surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose flaking paint. Dirt and chalk should be removed by power washing or hand scrubbing with an abrasive cleanser and water, followed by a clean water rinse. Mildew must be removed by washing the surface with a solution of one part household bleach mixed with six parts water. Rinse well with clean water following wash. Wax should be removed by solvent cleaning. Grease and oil should be cleaned by using CORONADO® Sur-Prep™ I. Rust must be removed by blasting, hand sanding vigorously or by conscientious power tool cleaning. Remove loose, flaking paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p>Priming – (new or bare surfaces): Wood – Use CORONADO® Exterior Latex Primers 410-11 or 9-11. For bleeding wood, such as redwood or cedar, it may be necessary to apply two coats of primer. Masonry – Use CORONADO® Primer/Sealer 48-11. To fill porous block, use 958-11 Latex Block Filler. Ferrous Metal – Use CORONADO® Metal Primers 35-111 or 36-11 Non-Ferrous Metal – Use CORONADO® 100-10 Galvanized – Use CORONADO® Primer 100-10 or 116-11</p> | |
| APPLICATION: | Stir product with a circular, lifting motion before you begin to paint. Acrylic Latex Flat House Paint may be applied by brush, spray, pad or roller, at a rate of application not to exceed 400 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" or 1/2" nap cover for smooth surfaces, a 3/4" nap cover for semi-rough surfaces and a 1" or 1 1/2" nap cover for rough surfaces. For spray application, thin with clean water, up to 20% reduction if necessary. Do not apply when surface or air temperatures are below 50° F. Do not apply to hot surfaces or in direct sunlight. Do not apply if rain is threatening. | |
| *NOTE ON SPREAD RATE: | Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate. | |

| | |
|-----------------------------|--|
| RESIN TYPE: | Acrylic |
| SOLIDS: | Weight: 51.5 ± 1.0% Volume: 36.6 ± 1.0% |
| WEIGHT PER GALLON: | 11.0 lbs. |
| VISCOSITY: | 95 – 100 KU (Krebs Units) |
| FLASH POINT: | 200° F. or greater (TT-P-141, Method 4293) |
| LIGHT REFLECTANCE: | 92% (White or lightest colors) |
| SPECULAR GLOSS: | 6 – 12 units @ 85 degrees |
| SAG RATING: | Pass 8 mils (Leneta) |
| REC. FILM THICKNESS: | Wet: 4.0 to 5.3 mils Dry: 1.5 to 2.0 mils |
| CAUTIONS: | <p style="text-align: center;">WARNING!</p> <p style="text-align: center;">OVEREXPOSURE MAY CAUSE KIDNEY DAMAGE. HARMFUL OR FATAL IF SWALLOWED. Causes eye irritation. Contains Ethylene Glycol</p> <p>Use only with adequate ventilation. Avoid breathing dust, vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes. Wash thoroughly after handling.</p> <p>First Aid: In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Get medical attention immediately. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting. Get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p>WARNING: This product contains chemicals known to the state of California to cause cancer, birth defects or other reproductive harm.</p> <p style="text-align: center;">Obtain and read the MSDS prior to using this product. KEEP OUT OF REACH OF CHILDREN</p> |
| VOC/VOS STATEMENT: | This product contains a maximum of 100 grams VOC/VOS per liter of coating. (.83 Pounds Per Gallon) |
| OTC CATEGORY: | This product is compliant under the Ozone Transport Commission regulations as a Flat Coating. |
| FEDERAL APPROVALS: | This product meets the performance requirements of TT-P-96 Type I, II or III and TT-P-1510. |

05/09